

Duradene®

TYPICAL PROPERTIES

DURADENE	A.O	BOUND STYRENE	VINYL	T _g	BASE ML/4	OE ML4	OIL PHR	OIL TYPE	SPECIFIC GRAVITY
706/HX263	N.S.	23.5	12	-62	55	--	0	--	0.93
711	S.S.	18.0	12	-70	70	--	0	--	0.93
738*	N.S.	20.0	58	-33	74	--	0	--	0.93
739*	N.S.	20.0	60	-34	92	--	0	--	0.93
741*	N.S.	5.0	28	-77	60	--	0	--	0.93
750B	S.	18.0	15	-70	103	45	37.5	High Viscosity Naphthenic	0.93
751B	S.	25.0	15	-60	110	45	37.5	High Viscosity Naphthenic	0.94
753B	S.	33.0	16	-50	130	75.5	20.0	High Viscosity Naphthenic	0.94
756B	S.	33.5	30	-35	125	57	37.5	High Viscosity Naphthenic	0.95
763B	S.	40.5	38.5	-22	137	59	37.5	High Viscosity Naphthenic	0.95

* Tin Coupled

May 2009



FIRESTONE POLYMERS

P.O. Box 26611, Akron, OH 44319-0006 • 1.800.282.0222 fax: 330.379.7875 www.firestonepolymers.com • E-mail: info@firestonepolymers.com